

Automotive Foam



Product code	Density	color	Hardness 50% [N]	Resilience	Applicable Standard	Application
018GYLG	18+/-1	Grey	140+/-20	35% min	IS7888, ASTM-3574	Automobiles Seat Covers with vinyl lamination Seat Covers with Textile Fabric lamination Car Door Trims Car upholstery
018GYFR	18+/-1	Grey	105+/-15	35% min	IS7888, FMVSS-302	
023GYFR	23+/-1	Grey	140+/-20	35% min	IS7888, FMVSS302, Cal-117,UL-94	
026GYFR	26+/-1	Grey	130+/-30	35% min	IS7888, FMVSS302, Cal-117,UL-94	
026GYRG	26+/-1	Grey	230+/-30	35% min	IS7888, ASTM-3574	
028GYFR	28+/-2	Grey	160+/-30	35% min	IS7888, FMVSS302, Cal-117,UL-94	Automobiles Door trims
028WHBS	28+/-2	White	170 +/-30	35% min	IS7888, FMVSS302, Cal-117,UL-94 BSS 5852 Crib5	
032GYFR	32+/-2	Grey	240+/-30	35% min	IS7888, ASTM-3574	
035YECL	35+/-2	Yellow	>500	30% min	IS7888, FMVSS-302	
035YEHR	35+/-2	Yellow	>500	30% min	IS7888	Automobiles Sun visors
035GYHR	35+/-2	Grey	>500	30% min	IS7888	
035GYCL	35+/-2	Grey	>500	30% min	IS7888,FMVSS-302	