

## Footwear Grade Foam



Product code	Density Kg/m <sup>3</sup>	Color	Hardness 50% [N]	Resilience	Applicable Standard	Application
023GYRG	23+/-1	Grey	220+/-30	30% min	IS7888,ASTM-3574	Shoe Shirner
023BKRG	23+/-1	Black	200+/-20	30% min	IS7888,ASTM-3574	
026WHRG	26+/-1	White	225+/-30	35% min	IS7888,ASTM-3574	Used is shoe sole
026LGFG	26+/-1	Light Grey	120+/-20	40% min	IS7888,ASTM-3574	Used in shoe upper and footwear sole
026GYFG	26+/-1	Grey	120+/-20	40% min	IS7888,ASTM-3574	
026BLFG	26+/-1	Blue	120+/-20	40% min	IS7888,ASTM-3574	
026BLFG	26+/-1	Blue	120+/-20	40% min	IS7888,ASTM-3574	
30BKFG	30+/-2	Grey	200+/-30	40% min	IS7888,ASTM-3574	
030LGFG	30+/-2	Light Grey	260+/-30	40% min	IS7888,ASTM-3574	
030GYFG	30+/-2	Grey	260+/-30	40% min	IS7888,ASTM-3574	
032WHRG	32+/-2	White	240+/-30	35% min	IS7888,ASTM-3574	
040WHRG	40+/-2	White	250+/-30	35% min	IS7888,ASTM-3574	
040GYFG	40+/-2	Grey	170+/-30	40% min	IS7888,ASTM-3574	
040LGFG	40+/-2	Light Grey	170+/-30	40% min	IS7888,ASTM-3574	
050BLFG	50+/-2	Blue	>500	30% min	IS7888	
050WHRG	50+/-2	White	290+/-50	40% min	IS7888	